

Fortaroute D758 Roadmarking Paint

Fortaroute D758 is a tried and tested fast-drying, short-term coating for ROAD MARKINGS on fresh tarmacadam surfaces. The excellent properties gives a durable and colour retentive finish.



Fortaroute D758 Roadmarking Paint is suitable for use on Roadways and parking areas in a variety of locations. A wide range of colours are available

McConnells **Fortaroute D758 Roadmarking Paint** will provide fast drying coloured short-term markings on new tarmacadam surfaces and permit fast re-opening time frames.

Fortaroute D758 Roadmarking Paint

Application: We would suggest that they are spray applied by experienced contractors when large areas are to be sprayed.

- Decorative and waterproof.
- Excellent light fastness.
- Fungus resistant.
- Easily maintained.
- Dries very quickly to a high sheen finish.
- Extensive range of RAL and BS colours available.
- Pls. refer to www.mcc.ie to view colour charts.

Packing

Fortaroute D758 Roadmarking Paint is supplied in 5/10 litre containers.

Preparation of surfaces

Ensure that concrete, brick or tarmac is dry and free from fungi, lichens and mosses. If organic growths of this type are present, the surface should be treated with two applications of a 5% solution of domestic bleach, followed when dry with the use of a stiff bristle brush to remove any loose materials. Alternatively, the surface may be power hosed, followed by one application of the 5% bleach solution. The paint may then be applied to the dry surface.

Application

Stir thoroughly before use. Apply 2 coats using air assisted or airless spray and working the paint well into the surface. On unpainted porous surfaces, we would suggest that first be thinned about 5-10% with McConnell's **Fortaclean 2263 Thinners** to ensure penetration. The second coat should be applied undiluted from the container.

Touch dry: >1hours
Recoatable: 3 hours
Fully hard: 7 days
(Assuming temperatures of 15°C and good air movement).

Drying time may be considerably extended in cold conditions, or during periods of high humidity.

Ambient conditions for painting

Dry conditions
Minimum Temperature: 5 C
Relative humidity: Max. 80%

Coverage

Coverage is approximately 7m² per litre per coat, depending on porosity of the surface. Two or more coats are normally required to provide a sufficient film build on ramps and marked areas.

Storage

Store in clean dry conditions.

Shelf Life

At least 24 months in correctly resealed container, in a cool, dry and frost-free location.

Cleaning Tools and Equipment

Always remove as much paint as possible from the application equipment before washing with McConnell's **Fortaclean 2263 Roadline Thinners**. Do not empty paint into drains or water courses. Empty containers are non-hazardous, but should be disposed of in accordance with local and national regulations. Most local authorities have facilities for disposal of paint waste and used paint tins.

General Maintenance

General cleaning should be carried out with a neutral cleaner.

Safety

Fortaroute D758 Roadmarking Paint and McConnell's 2263 Thinners are classed as hazardous for supply or for transport. Flash point: -10 degrees centigrade, highly flammable. Please refer to our Material Safety Data Sheet for information.

McConnells Fortaclean 2263 Thinners

2263 is special solvent blend specifically developed for use to dilute **Fortaroute D758 Roadmarking Paint** and to clean equipment used in its application.

Ordering

All of our products are available direct from McConnell's and are sold subject to McConnell's Standard Conditions of Sale.

The Company and its employees are often asked on potential uses of McConnell's products in addition to those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by McConnell's. The Customer/User must always test our product in their particular application to satisfy themselves that their requirement is fulfilled before proceeding with their project.

Manufactured by



International Coatings Limited
The Enterprise Centre, Ballycorus,
Kiltarnan, Dublin 18.
Tel: 01 2822877 Fax: 01 2822653