

# Fortacoat Q787 Fluorescent Paint

**Fortacoat Q787 is a tried and tested fluorescent paint for application to Wood, Metal and Masonry surfaces.**



**Fortacoat Q787 Fluorescent Paint is suitable for use on bridges, bollards, bicycles, ships etc....**


McConnells **Fortacoat Q787 Fluorescent Paint** enhances the visibility of the items coated during the daytime and at night time. **Fortacoat Q787 Fluorescent Paint** can be applied by an individual with DIY painting experience.

New coatings of **Fortacoat Q787 Fluorescent Paint** should be applied over a white primer coating such as **Fortacryl E250**.

- High Visibility and may be protected with a clear glaze.
- Excellent light fastness.
- Fungus resistant.
- Easily maintained.
- Dries quickly to a Matt finish.
- Four standard colours available.




Orange



Red



Green



Yellow

### Packing

**Fortacoat Q760 Fluorescent Paint** is supplied in 2.5lt & 5 litre containers.

### Preparation of surfaces

Ensure that the wood, metal or masonry is dry and free from fungi, lichens and mosses. If organic growths of this type are present, the surface should be treated with two applications of a 5% solution of domestic bleach, followed when dry with the use of a stiff bristle brush to remove any loose materials. Alternatively, the substrate may be power hosed, followed by one application of the 5% bleach solution. The paint may then be applied to the dry surface.

### Application

Stir thoroughly before use. Apply over a compatible base white paint such as Fortacryl E250 primer to achieve best colour effect. Apply 1 or 2 coats for opacity as necessary using a brush spray or roller.

Touch dry: 3 hours  
Recoatable: 12 hours  
Fully hard: 7 days  
(assuming temperatures of 15°C and good air movement).

Drying time may be considerably extended in cold conditions, or during periods of high humidity.

### Ambient conditions for painting

Dry conditions  
Minimum Temperature: 5 C  
Relative humidity: Max. 80%

### Coverage

Coverage is approximately 13m<sup>2</sup> per litre per coat, depending on porosity of the surface. Two coats may be required as detailed under "Application".

### Storage

Store in clean dry conditions.

### Shelf Life

At least 24 months in correctly resealed container, in a cool, dry and frost-free location.

### Cleaning Tools and Equipment

Always remove as much paint as possible from the application equipment before washing with McConnell's **Fortaclean A156 Thinners**. Do not empty paint into drains or water courses. Empty containers are non-hazardous, but should be disposed of in accordance with local and national regulations. Most local authorities have facilities for disposal of paint waste and used paint tins.

### General Maintenance

General cleaning should be carried out with a neutral cleaner.

### Safety

**Fortacoat Q787 Fluorescent Paint and McConnell's A156**

**Thinners** are classed as hazardous for supply or for transport.

Flash point: >23 degrees centigrade.

Please refer to our Material Safety Data Sheet for information.

## McConnells Fortaclean A156 Thinners

**A156** is special solvent blend specifically developed for use to dilute **Fortacoat Q787** Fluorescent Paint and to clean equipment used in its application.

### Ordering

All of our products are available direct from McConnell's and are sold subject to McConnell's Standard Conditions of Sale.

The Company and its employees are often asked on potential uses of McConnell's products in addition to those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by McConnell's. The Customer/User must always test our product in their particular application to satisfy themselves that their requirement is fulfilled before proceeding with their project.

Manufactured by



**International Coatings Limited**  
The Enterprise Centre, Ballycorus,  
Kiltiernan, Dublin 18.  
Tel: 01 2822877 Fax: 01 2822653