



International Coatings Limited
The Enterprise Centre, Ballycorus,
Kiltarnan, Dublin 18.
Tel: 01 2822877 Fax: 01 2822653
www.mcc.ie e-mail: sales@mcc.ie

August 30, 2013

Draft specification for the coating of New Galvanised Ducting in a Swimming Pool Area.

Prepare the surface to be coated as follows:

- 1) Solvent wipe the galvanised substrates thoroughly with Fortaclean A156 thinners to remove contaminants and allowed to dry.
- 2) Remove any loose particles.
- 3) Apply a coating of Temacoat GPLS primer RAL 7015 and allow to dry thoroughly. Apply by spray application with the paint diluted approximately 25% with Fortaclean A214 thinners. To achieve good adhesion apply in three "miss-coats" in order to provide an even film.
- 4) Apply two coats of Fortachlor Q734 RAL (of colour choice) as a top coating at approx 7 square meters per litre.

(Temacoat GPLS and Fortachlor Q734 are available in a range of BS, RAL, and NCS colours- see colour selection on www.mcc.ie)

Application of Temacoat GPLS and Temadur 90 to be as per manufactures instructions contained in the relevant Data sheets, available from McConnells.

Please consult with McConnell Coatings (www.mcc.ie) regarding volumes required for the area to be coated.

All of our products are available direct from McConnells and are sold subject to the Company's Standard Conditions of Sale.

The Company and its employees are often asked on potential uses of McConnell's products in addition to those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by McConnells. The Customer/User must always test our product in their particular application to satisfy themselves that their requirement is fulfilled before proceeding with their project.